



K60000 Series Gloss Cast Vinyl

KPMF 60000 Series Cast Vinyl films are speciality PVC films formulated using novel resin and pigment technology to offer an economically priced range of cast vinyls.

The range is limited to Black and White and has been carefully formulated to ensure excellent CAD/CAM cutting and weeding properties. They are recommended for use in window graphics and equipment identification and for road signs and all general sign applications requiring an outstanding outdoor life when applied to flat surfaces.

CHARACTERISTIC	TEST METHOD	TYPICAL VALUE
Film Thickness	ISO 4591:1992	0.057mm
Adhesive Thickness	ISO 4591:1992	0.028mm
Adhesive Type		Clear Permanent Cross-Linking Acrylic
Release Liner		140gsm Stayflat Kraft Printed Green
Storage		Two years, out of direct sunlight at 23°C and 50% humidity
Tensile	ISO 527:1996	>12.0 N/mm ²
Elongation	ISO 527:1996	>50%
Adhesion 20 Mins/90°	FINAT FTM2/Stainless Steel	460 N/Metre
Adhesion 20 Mins/180°	FINAT FTM1/Stainless Steel	590 N/Metre
Adhesion 24 Hrs/180°	FINAT FTM1/Stainless Steel	740 N/Metre
Static Shear (25 x 25mm)	FINAT FTM8/Stainless Steel	>16 hours
Dimensional Stability (150 x 150mm/48 hours/70°C)	FTM14/Aluminium	<0.4mm
Gloss 60°	ASTM 523-89	>85%
Flammability		Self Extinguishing
Artificial Weathering	QUV	>1,000 hours
Weathering	Vertical Exposure/Mid Europe	
Black		12 years
White		10 years
Rivet Testing	KPMF ST 22	N/A
Application Temperature	Clean, dry surface	+8°C to 25°C
Service Temperature		-40°C to + 105°C
Adhesion Properties to Various Substrates for 24 hours at 23°C/180° Peel		
Aluminium - Untreated		950 N/Metre
Aluminium - Anodised		970 N/Metre
Stainless Steel		800 N/Metre
Chromed Steel		740 N/Metre
Polyurethane		460 N/Metre
Glass		820 N/Metre
Acrylic Sheet		820 N/Metre
ABS Sheet		790 N/Metre
Resistance to various liquids after application and conditioned for 24 hours at 23°C. Results examined 1 hour after test.		
Humidity	24 hours at 38°C and 100%	No Effect
Water (Distilled)	24 hours at 32°C	No Effect
Sea Water	1 year Mid Tide (BS 5609:1986)	No Effect
Reference Fuel	1 hour at 23°C	Very Slight Film Softening
Diesel Fuel	1 hour at 23°C	No Effect
SAE Motor Oil	24 hours at 23°C	No Effect
Antifreeze/Water (1:1)	24 hours at 23°C	No Effect
Detergent Solution	8 hours at 65°C	No Effect
Hydraulic Oil	24 hours at 23°C	No Effect
Battery Acid	24 hours at 23°C	No Effect
Although we have good control of the colour production at KPMF, it is advisable to avoid using different batches of material for the same end application		

KPMF films should not be applied to unsound surfaces or to surfaces which may subsequently crack, peel, outgas or are of low surface energy. It is recommended that any application surface should have an energy level in excess of 40 dyne/cm. (Polyolefins should be in excess of 45 dyne/cm). The above data shows typical properties and should not be taken as a guarantee for performance. Purchasers should determine the suitability of each product prior to its intended use. Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Durability is based on middle European exposure conditions. Actual performance will depend on substrate preparation, exposure conditions and application of marking.

IMPORTANT

Kay Premium Marking Films are produced under stringent manufacturing conditions. The information and typical values shown are based upon research believed to be reliable and are provided without guarantee and do not constitute a warranty. The values are not for use in specifications. Ink and paint systems can affect the performance of film and also the adhesive properties, as can application techniques. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use.

WARRANTY

Kay Premium Marking Films are produced under careful quality control and are warranted to be fit for the purpose and free from defect in material and workmanship. Any material shown to be defective to our satisfaction at the point of sale shall be replaced free of charge. Kay Premium Marking Films Limited liability to the purchaser shall in no circumstances exceed the cost of the amount of the defective material supplied.