

## K75200 Series Cast Overlaminates Vinyl

### Product Description

These premium quality cast vinyl films have been designed for over lamination of KPMF films.

The 30-micron clear over laminate, available in a gloss or matt version, offers enhanced stabilisation to ensure optimum exterior durability and protection from the harmful effects of UV and other environmental contaminants.

The liner is single sided polyethylene coated which ensures excellent lay flat characteristics in a variety of environments.

### Recommended Uses

- Overlaminates vinyl

### Products Available

- K75202 Gloss Clear Cast Over laminate (30µm)
- K75203 Matt Clear Cast Over laminate (30µm)

### Face Film

30µm Cast

### Adhesive

25g/m<sup>2</sup> clear permanent solvent-based acrylic

### Release Liner

Single-sided PE

### Widths

1524mm

### Durability

7 years outdoors  
(vertical exposure, mid-Europe)

### Shelf Life

2 years  
(out of direct sunlight, between 15°C and 23°C, 30% to 70% relative humidity)

### Physical Characteristics

	Test Method	Typical Value
Film Thickness	ISO 4591:1992	30µm
Elongation	ISO 527-3:2018	>75%
Dimensional Stability (48 hours/70°C)	FTM14/Aluminium	< 0.4mm
Gloss 60°	ASTM D523-14:2018	Matt <25 Gloss >85
20 minute 180° Peel	FTM1/Painted Steel	>450N/m
24 hour 180° Peel	FTM1/Painted Steel	>530N/m
Flammability		Self-extinguishing
Artificial Weathering	Xenon Arc	2000 hours
Outdoor Weathering	Vertical Exposure/Mid Europe	7 years

### Temperature Range

Application Temperature	Minimum +10°C
Service Temperature	-40°C to +90°C

### Resistance to various liquids after application and conditioned for 24 hours at 23°C. Results examined 1 hour after test

Humidity	24 hours at 38°C and 100%	No effect
Water (Distilled)	24 hours at 32°C	No effect
Diesel Fuel	1 hour at 23°C	No effect
SAE Motor Oil	24 hours at 23°C	No effect
Antifreeze/Water (1:1)	24 hours at 23°C	No effect

---

## Product Usage Guide

KPMF films should not be applied to unsound surfaces or to surfaces which may subsequently crack, peel, outgas or are of low surface energy. It is recommended that any application surface should have an energy level in excess of 40 dyne/cm. (Polyolefins should be in excess of 45 dyne/cm).

Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids etc. may eventually cause deterioration. Actual performance will depend on substrate preparation, exposure conditions and application of marking.

Although we have good control of the colour production of KPMF products at our multiple locations, as with all other manufacturer's products, customers should be aware that there may be subtle variances between samples, swatches and production materials, so therefore it is advisable to avoid using different batches of material for the same end application to avoid possible colour shifts between the batches.

Application temperature onto clean, dry surface Min +10°C

---

### Product Warranty

*Kay Premium Marking Films are produced under stringent manufacturing conditions. The information and typical values shown are based upon research believed to be reliable and are provided without guarantee and do not constitute a warranty. The values are not for use in specifications. Ink and paint systems can affect the performance of film and also the adhesive properties, as can application techniques. Users are advised to ensure that performance and reliability are not compromised by determining the suitability of each product prior to its intended use.*

*Kay Premium Marking Films are produced under careful quality control and are warranted to be fit for the purpose and free from defect in material and workmanship. Any material shown to be defective to our satisfaction at the point of sale shall be replaced free of charge. Kay Premium Marking Films Limited liability to the purchaser shall in no circumstances exceed the cost of the amount of the defective material supplied. This product has been warranted to provide clean removability, under controlled conditions, up to a period of three years from a range of substrates. Clean removability is deemed with less than 30% adhesive residue when using heat and chemical removal methods. Exceptions to the removal warranty are those applied to the following: pre-existing graphics, paint which is not properly bonded to the substrate and custom paint applications. There is no guarantee made for; ease or speed of graphic removal, removal from improperly cured paint, removal from oxidized or chalked substrates, or from horizontally exposed outdoor applications. Due to the large variety of available paint finishes, it is advisable to fully evaluate small areas particularly after printing prior to complete applications.*

*The data included on the Data sheet shows typical properties and should not be taken as a guarantee for performance.*

ISO 9001 · IATF 16949